



■ Carthage 6%™

Carthage 6% is a woven filtration geotextile made of high-tenacity, monofilament polypropylene yarns which are woven into a stable network such that they retain their relative position and then calendered. Carthage 6% is part of the [Carthage % Open Area Series](#) of woven monofilament filtration geotextiles, is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

AASHTO M 288-06: Carthage 6% meets the geotextile requirements of Classes 2 and 3, <50% elongation (Percent 'in-situ' soil passing 0.075 mm: Both 15-50% and >50%) for Subsurface Drainage; and Class 2, <50% elongation (Percent 'in-situ' soil passing 0.075 mm: Both 15-50% and >50%) for Permanent Erosion Control.

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
<input type="checkbox"/> Mechanical			
Grab Tensile Strength	ASTM D 4632	1.65 x 1.11 kN	370 x 250 lbs
Grab Tensile Elongation		15%	
Wide Width Tensile Strength	ASTM D 4595	39.41 x 25.40 kN/m	225 x 145 lbs/in 2700 x 1740 lbs/ft
Trapezoidal Tear	ASTM D 4533	0.45 x 0.27 kN	100 x 60 lbs
CBR Puncture	ASTM D 6241	4.23 kN	950 lbs
<input type="checkbox"/> Endurance			
UV Resistance	ASTM D 4355	90% @ 500 hrs	
<input type="checkbox"/> Hydraulics / Filtration			
Permittivity ⁽¹⁾	ASTM D 4491	0.28 sec ⁻¹	
Water Flow Rate ⁽¹⁾		733 lpm/m ²	18 gpm/ft ²
Percent Open Area	CW-02215	4-6%	
Apparent Opening Size (AOS) ⁽¹⁾	ASTM D 4751	0.212 mm	70 US Std. Sieve
<input type="checkbox"/> Physical			
Standard Roll Sizes / Packaging / Weight (Custom fabrication and packaging are available.)	Measured (Typical)	1.83 m x 91.44 m 167.2 m ² 45.4 kg	6.0 ft x 300 ft 200 yd ² 100 lbs
		3.65 m x 91.44 m 334.4 m ² 82.1 kg	12.0 ft x 300 ft 400 yd ² 181 lbs

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288-06 and has been replaced with CBR Puncture ASTM D 6241.

- ⁽¹⁾ At the time of manufacturing. Handling, storage and shipping may change these properties.
- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
 - The properties reported above are effective 01-01-16 and are subject to change without notice.

» [AASHTO M 288-06: Geotextile Product Selection Guide](#)

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.